

Quadrant EPP PPO Polyphenylene oxide, unfilled, extruded (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO

Material Notes:

Data provided by Quadrant Engineering Plastic Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-PPO-Polyphenylene-oxide-unfilled-extruded-ASTM-Product-Data-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	Immersion, 24hr; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	92	92	ASTM D785
Tensile Strength	57.2 MPa	8300 psi	ASTM D638
Elongation at Break	23 %	23 %	ASTM D638
Tensile Modulus	2.53 GPa	367 ksi	ASTM D638
Flexural Strength	88.9 MPa	12900 psi	ASTM D790
Flexural Modulus	2.74 GPa	397 ksi	ASTM D790
Compressive Strength	91.0 MPa	13200 psi	10% Def.; ASTM D695
Compressive Modulus	2.18 GPa	316 ksi	ASTM D695
Shear Strength	57.2 MPa	8300 psi	ASTM D732
Izod Impact, Notched	1.55 J/cm	2.90 ft-lb/in	ASTM D256 Type A

Thermal Properties	Metric	English	Comments
CTE, linear	64.1 $\mu\text{m}/\text{m}\cdot\text{°C}$	35.6 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM E831
	@Temperature -40.0 - 149 °C	@Temperature -40.0 - 300 °F	
Maximum Service Temperature, Air	93.3 °C	200 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	127 °C	260 °F	ASTM D648
Glass Transition Temp, Tg	140 °C	284 °F	ASTM D3418
Flammability, UL94	V-1	V-1	1/8 inch (Estimated Rating)

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1e+13 ohm	>= 1e+13 ohm	EOS/ESD S11.11
Dielectric Strength	27.6 kV/mm	701 kV/in	Short Term; ASTM D149

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Unacceptable	Unacceptable	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Unacceptable	Unacceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Unacceptable	Unacceptable	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Limited	Limited	
Hydrocarbons - Aromatic	Unacceptable	Unacceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Unacceptable	Unacceptable	

Descriptive Properties	Value	Comments
Color	Black	
Machinability	6	1-10, 1=Easier to Machine

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China