

Quantum Composites QC-2150 50% Glass Reinforced Phenolic SMC

Category: Polymer, Thermoset, Composite SMC, Phenolic, Phenolic/Glass Fiber SMC

Material Notes:

QC-2150 is a glass reinforced phenolic engineered structural composite molding compound. It exhibits outstanding low flammability characteristics. QC-2150 is recommended for applications such as aircraft interiors and public transportation components requiring composite materials having very low flammability, low smoke, and minimal generation of toxic gasses. Form = Rolled SheetColor = Natural, BlackGlass Fiber Content = 50% nominalInformation provided by Quantum Composites.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quantum-Composites-QC-2150-50-Glass-Reinforced-Phenolic-SMC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.82 g/cc	1.82 g/cc	ASTM D792
Linear Mold Shrinkage	0.0015 cm/cm	0.0015 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	227 MPa	32900 psi	ASTM D638
Flexural Strength	358 MPa	51900 psi	ASTM D790
Flexural Modulus	21.0 GPa	3050 ksi	ASTM D790
Izod Impact, Notched	6.40 J/cm	12.0 ft-lb/in	ASTM D256

Processing Properties	Metric	English	Comments
Shelf Life	2.00 Month	2.00 Month	
	@Temperature 4.44 °C	@Temperature 40.0 °F	
	6.00 Month	6.00 Month	
	@Temperature -17.8 °C	@Temperature 0.000 °F	

Descriptive Properties	Value	Comments
Fiber Length (in)	1	Glass, nominal

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058



Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China