

Quantum Nylon 6/6 MoS2 Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, MoS2 Filled

Material Notes:

Information provided by Quantum Advanced Engineering Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quantum-Nylon-66-MoS2-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.16 g/cc	1.16 g/cc	ASTM D792
Water Absorption	1.0 %	1.0 %	ASTM D570
Water Absorption at Saturation	8.5 %	8.5 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	85	85	ASTM D785
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength	82.7 MPa	12000 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Tensile Modulus	3.28 GPa	475 ksi	ASTM D638
Flexural Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	3.31 GPa	480 ksi	ASTM D790
Compressive Strength	110 MPa	16000 psi	ASTM D695
Compressive Modulus	2.90 GPa	420 ksi	ASTM D695
Shear Strength	72.4 MPa	10500 psi	ASTM D732
Izod Impact, Notched	0.374 J/cm	0.700 ft-lb/in	ASTM D256
Coefficient of Friction	0.25	0.25	

Thermal Properties	Metric	English	Comments
CTE, linear	72.0 - 79.2 $\mu\text{m}/\text{m}\cdot\text{°C}$	40.0 - 44.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM D696
Thermal Conductivity	0.245 W/m-K	1.70 BTU-in/hr-ft ² -°F	ASTM C177
Melting Point	260 °C	500 °F	ASTM D3417
Maximum Service Temperature, Air	104 °C	220 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	143.3 °C	270 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	93.3 °C	200 °F	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	ASTM D257
Dielectric Constant	3.8	3.8	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	13.8 kV/mm	350 kV/in	ASTM D149
Dissipation Factor	0.020	0.020	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Descriptive Properties	Value	Comments
FDA Compliance	no	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China