

Radici Radiflam® S RV250FR (dry) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 20% Glass Fiber Filled

Material Notes:

Radiflam® S is a range of flame retardant polyamides 6 (PA 6) used for injection molding and extrusion for all applications where high fire resistance is required. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radiflam-S-RV250FR-dry-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	
Water Absorption	2.5 %	2.5 %	
Moisture Absorption at Equilibrium	1.1 %	1.1 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	140 MPa	20300 psi	
Elongation at Break	1.8 %	1.8 %	
Tensile Modulus	14.3 GPa	2070 ksi	
Charpy Impact Unnotched	2.30 J/cm ²	10.9 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	3.00 J/cm ²	14.3 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.450 J/cm ²	2.14 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Flammability, UL94	V-0	V-0	
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00 \times 10^{11}$ ohm-cm	$\geq 1.00 \times 10^{11}$ ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China