

Radici Radilon® A ERV3012 (cond.) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-A-ERV3012-cond-Nylon-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	(Dry)
Water Absorption	6.7 %	6.7 %	initially dry
Moisture Absorption at Equilibrium	1.8 %	1.8 %	initially dry

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	77.0 MPa	11200 psi	
Elongation at Break	7.5 %	7.5 %	
Tensile Modulus	4.10 GPa	595 ksi	
Charpy Impact Unnotched	8.00 J/cm ²	38.1 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	2.00 J/cm ²	9.52 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	550 V	550 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China