

Radici Radilon® A RCV3015 RKC Nylon 66-GF30

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 30% Glass Fiber Filled

Material Notes:

Automotive cooling liquid resistant PA66-GF30 grade designed to be processed by GIT technology. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-A-RCV3015-RKC-Nylon-66-GF30.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	123 MPa	17800 psi	ISO 527
Elongation at Break	2.3 %	2.3 %	ISO 527
Tensile Modulus	6.65 GPa	965 ksi	ISO 527
Flexural Modulus	6.10 GPa	885 ksi	ISO 178

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Flammability, UL94	HB @Thickness 1.00 mm	HB @Thickness 0.0394 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China