

## Radici Radilon® A RV300RKC (cond.) Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

**Material Notes:**

Radilon® A is a range of polyamide 66 (PA66) products obtained through the polymerization of hexamethylenediamine and adipic acid, and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Radilon-A-RV300RKC-cond-Nylon-66.php](http://www.lookpolymers.com/polymer_Radici-Radilon-A-RV300RKC-cond-Nylon-66.php)

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	140 MPa	20300 psi	
Elongation at Break	6.0 %	6.0 %	
Tensile Modulus	7.50 GPa	1090 ksi	
Charpy Impact Unnotched	9.00 J/cm <sup>2</sup>	42.8 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	11.0 J/cm <sup>2</sup>	52.3 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.20 J/cm <sup>2</sup>	5.71 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.80 J/cm <sup>2</sup>	8.57 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	550 V	550 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China