

## Ravago Manufacturing Americas Hylon® N1013THL Nylon 6/6 (DAM)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized

### Material Notes:

Information provided by Ravago.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ravago-Manufacturing-Americas-Hylon-N1013THL-Nylon-66-DAM.php](http://www.lookpolymers.com/polymer_Ravago-Manufacturing-Americas-Hylon-N1013THL-Nylon-66-DAM.php)

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.70 %	0.70 %	24 hrs; ASTM D570
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	0.125 in; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	82	82	ASTM D785
Tensile Strength at Break	96.5 MPa	14000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	159 MPa	23000 psi	ASTM D790
Flexural Modulus	3.96 GPa	575 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm	2.50 ft-lb/in	73°F; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	122 µm/m-°C	68.0 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	232 °C	450 °F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Strength	20.9 kV/mm	530 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Melt Temperature	282 - 299 °C	540 - 570 °F	
Mold Temperature	65.6 - 98.9 °C	150 - 210 °F	

<small>Drying Temperature</small> Processing Properties	73.9 °C Metric	165 °F English	Comments
Dry Time	2 - 4 hour	2 - 4 hour	
Moisture Content	0.18 %	0.18 %	
Back Pressure	0.138 - 0.414 MPa	20.0 - 60.0 psi	
Screw Speed	40 - 120 rpm	40 - 120 rpm	

Descriptive Properties	Value	Comments
Holding Pressure	750 to 1400 psi	
Injection Rate	Fast	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China