

Resin Technology Group 401 Oxy-Bond™ Electrically Conductive Epoxy Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive , Epoxy, Electrically Conductive

Material Notes:

Oxy-Bond and Millenium Adhesive Systems Engineered for strength, durability, lightness, and formability, our Oxy-Bond and Millenium lines offer adhesives with physical and electrical properties to match a variety of specific application parameters, including MIL-APPROVED.

Custom designed bonding products and expert technical assistance are always available. Resin Technology Group 401 Oxy-Bond™

Electrically Conductive Epoxy Adhesive Room temperature curing, two part silver conductive epoxy.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resin-Technology-Group-401-Oxy-Bond-Electrically-Conductive-Epoxy-Adhesive.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 240 min	1.00 - 4.00 hour	
	@Temperature 65.0 °C	@Temperature 149 °F	
	1440 min	24.0 hour	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Pot Life	90 min	90 min	
	90 min	90 min	

Descriptive Properties	Value	Comments
Viscosity	Smooth Paste	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China