

Resinoid 2002-C5 Phenolic Molding, Fabric Reinforced

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic , Phenolic, Novolac, Fabric Filled

Material Notes:

Data provided by the manufacturer. The Resinoid 2000 organic fiber reinforced series compounds feature mechanical strength, dimensional stability, and shock resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resinoid-2002-C5-Phenolic-Molding-Fabric-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	ASTM D792A
Water Absorption	0.70 %	0.70 %	24 hours R.T. ASTM D570
Linear Mold Shrinkage	0.0025 cm/cm	0.0025 in/in	Positive Mold; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	98	98	ASTM D785
Tensile Strength, Ultimate	48.0 MPa	6960 psi	ASTM D651
Flexural Strength	97.0 MPa	14100 psi	ASTM D790
Compressive Strength	152 MPa	22000 psi	ASTM D695
Izod Impact, Notched	1.444 J/cm	2.705 ft-lb/in	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ASTM D648

Processing Properties	Metric	English	Comments
Mold Temperature	150 - 175 °C	302 - 347 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China