

RheTech Products T40P100-774UVA 40% Talc Reinforced Polypropylene, UV Stabilized, JA6A Black

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Applications: Wire trough Brackets Consoles Fan shrouds Fuse panel box Door cup pulls Injection molding conditions reported in table. Information provided by RheTech Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_RheTech-Products-T40P100-774UVA-40-Talc-Reinforced-Polypropylene-UV-Stabilized-JA6A-Black.php

| Physical Properties | Metric | English | Comments |
|-----------------------|---|---|--------------------|
| Specific Gravity | 1.27 g/cc | 1.27 g/cc | 23/23°C; ASTM D792 |
| Filler Content | 40 % | 40 % | ASTM D5630 |
| Linear Mold Shrinkage | 0.0090 cm/cm | 0.0090 in/in | ASTM D955 |
| Melt Flow | 15 g/10 min @Load 2.16 kg, Temperature 230 °C | 15 g/10 min @Load 4.76 lb, Temperature 446 °F | ASTM D1238 |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|------------------------------------|--|---------------------|
| Hardness, Shore D | 72 | 72 | ASTM D2240 |
| Tensile Strength at Break | 27.6 MPa | 4000 psi | 2 in/min; ASTM D638 |
| Flexural Modulus | 3.62 GPa | 525 ksi | Tangent; ASTM D790 |
| Izod Impact, Notched | 0.267 J/cm @Temperature 23.0 °C | 0.500 ft-lb/in @Temperature 73.4 °F | ASTM D256 |
| Gardner Impact | 0.904 J | 0.667 ft-lb | ASTM D5420 |

| Thermal Properties | Metric | English | Comments |
|---|---------|---------|-----------|
| Deflection Temperature at 0.46 MPa (66 psi) | 129 °C | 265 °F | ASTM D648 |
| Deflection Temperature at 1.8 MPa (264 psi) | 79.4 °C | 175 °F | ASTM D648 |

| Processing Properties | Metric | English | Comments |
|---------------------------|--------------|--------------|----------|
| Rear Barrel Temperature | 210 - 238 °C | 410 - 460 °F | |
| Middle Barrel Temperature | 216 - 243 °C | 420 - 470 °F | |

| Front Barrel Temperature Processing Properties | 221 - 249 °C Metric | 430 - 480 °F English | Comments |
|---|------------------------|-------------------------|-------------|
| Nozzle Temperature | 227 - 238 °C | 440 - 460 °F | |
| Mold Temperature | 26.7 - 48.9 °C | 80.0 - 120 °F | |
| Drying Temperature | 65.6 - 82.2 °C | 150 - 180 °F | |
| Dry Time | 1 - 2 hour | 1 - 2 hour | |
| Moisture Content | <= 0.050 % | <= 0.050 % | Recommended |
| Injection Pressure | 2.76 - 10.3 MPa | 400 - 1500 psi | |
| Hold Pressure | 2.07 - 8.27 MPa | 300 - 1200 psi | |
| Back Pressure | 0.345 - 1.03 MPa | 50.0 - 150 psi | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China