

Rochling Engineered Plastics Polystone® Reprocessed (UHMW-PE)

Category: Polymer, Thermoplastic, Polyethylene (PE), HDPE, High Density Polyethylene (HDPE), UHMW PE Ultra High Molecular Weight

Material Notes:

Polystone® M is a highly versatile polymer that features: Low coefficient of friction Excellent abrasion resistance High-impact strength Chemical resistance Complies with FDA regulations under the Food, Drug and Cosmetic Act of 1958 Approval by the USDA for meat and poultry handling applications Broad temperature range (-450 - 180°F) Little or no moisture absorption Noise resistance Easy machinabilityInformation provided by Röchling Engineered Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Rochling-Engineered-Plastics-Polystone-Reprocessed-UHMW-PE.php

Physical Properties	Metric	English	Comments
Density	0.935 g/cc	0.0338 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	63 - 69	63 - 69	ASTM D785
Tensile Strength, Yield	20.7 MPa	3000 psi	ASTM D638
Elongation at Break	290 %	290 %	ASTM D638
Izod Impact Resistance	9.60 J/cm ²	45.7 ft-lb/in ²	@ 73°F; ASTM D420-96
Coefficient of Friction, Static	0.10 - 0.20	0.10 - 0.20	Dynamic Coefficient @ 73°F on steel
Abrasion	90	90	Volumetric abrasion loss, %, relative to Natural Grade (100%)

Thermal Properties	Metric	English	Comments
CTE, linear	190 μm/m-°C	106 μin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	135 - 138 °C	275 - 280 °F	ASTM D789
Maximum Service Temperature, Air	82.2 °C	180 °F	Continuous

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+16 ohm-cm	>= 1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	35.4 kV/mm	899 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com



Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China