

Rotuba H Cellulose Acetate

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Cellulose Acetate, Molded

Material Notes:

Property values at 50% RH.Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Rotuba-H-Cellulose-Acetate.php

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in ³	ASTM D792
Water Absorption	2.3 %	2.3 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	76	76	ASTM D785
Tensile Strength, Ultimate	40.0 MPa	5800 psi	ASTM D638
Tensile Strength, Yield	30.0 MPa	4350 psi	ASTM D638
Elongation at Break	39 %	39 %	ASTM D638
Flexural Yield Strength	46.0 MPa	6670 psi	ASTM D790
Flexural Modulus	0.120 GPa	17.4 ksi	ASTM D790
Izod Impact, Notched	2.08 J/cm	3.90 ft-lb/in	ASTM D256
	0.590 J/cm	1.11 ft-lb/in	ASTM D256
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	155 °C	311 °F	Flow temperature, ASTM D569

Processing Properties	Metric	English	Comments
Processing Temperature	210 °C	410 °F	Center barrel temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China