

SABIC Innovative Plastics Cycolac® CRT3370 ABS (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 20% Glass Fiber Filled

Material Notes:

CYCOLAC CRT3370 is a 17% glass reinforced injection moulding grade of ABS. It exhibits high rigidity and excellent dimensional stability combined with medium/high heat performance and good flow characteristics. It isThis data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycolac-CRT3370-ABS-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	1.0 % @Temperature 23.0 °C	1.0 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	on tensile bar; SABIC Method
Melt Flow	14 g/10 min @Load 10.0 kg, Temperature 220 °C	14 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133
	14 g/10 min @Load 10.0 kg, Temperature 220 °C	14 g/10 min @Load 22.0 lb, Temperature 428 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	117	117	ISO 2039-2
Hardness, H358/30	120 MPa	17400 psi	ISO 2039-1
Tensile Strength at Break	62.0 MPa	8990 psi	5 mm/min; ISO 527
	67.0 MPa	9720 psi	50 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
	2.0 %	2.0 %	50 mm/min; ISO 527
Tensile Modulus	5.10 GPa	740 ksi	1 mm/min; ISO 527
Flexural Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	4.70 GPa	682 ksi	2 mm/min; ISO 178
	6.00 kJ/m ²	2.86 ft-lb/in ²	

Izod Impact, Notched (ISO) Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	80*10*4; ISO 180/1A Comments
	7.00 kJ/m ² @Temperature 23.0 °C	3.33 ft-lb/in ² @Temperature 73.4 °F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	20.0 kJ/m ² @Temperature 23.0 °C	9.52 ft-lb/in ² @Temperature 73.4 °F	80*10*4; ISO 180/1U
Charpy Impact, Notched	0.600 J/cm ² @Temperature -30.0 °C	2.86 ft-lb/in ² @Temperature -22.0 °F	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA
	0.700 J/cm ² @Temperature 23.0 °C	3.33 ft-lb/in ² @Temperature 73.4 °F	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA
Taber Abrasion, mg/1000 Cycles	35 @Load 1.00 kg	35 @Load 2.20 lb	CS-17; SABIC Method

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	40.0 µm/m-°C @Temperature 23.0 - 60.0 °C	22.2 µin/in-°F @Temperature 73.4 - 140 °F	ISO 11359-2
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ISO 8302
Hot Ball Pressure Test	<= 100 °C	<= 212 °F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	101 °C	214 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	96.0 °C	205 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	101 °C	214 °F	Rate B/50; ISO 306
	103 °C	217 °F	Rate B/120; ISO 306
UL RTI, Electrical	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical with Impact	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical without Impact	60.0 °C	140 °F	UL 746B
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	UL 94
	HB @Thickness 2.50 mm	HB @Thickness 0.0984 in	2nd value; UL 94
	650 °C	1200 °F	Glow Wire Flammability Index; IEC

Glow Wire Test Thermal Properties	Metric @ Thickness 3.20 mm	English @ Thickness 0.126 in	60695-2-12 Comments
--------------------------------------	-------------------------------	---------------------------------	------------------------

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	2.6	2.6	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	2.7	2.7	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	18.0 kV/mm	457 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dielectric Strength	26.0 kV/mm	660 kV/in	in oil; IEC 60243-1
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Dielectric Strength	35.0 kV/mm	889 kV/in	in oil; IEC 60243-1
	@Thickness 0.800 mm	@Thickness 0.0315 in	
Dissipation Factor	0.0040	0.0040	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dissipation Factor	0.0080	0.0080	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	450 V	450 V	IEC 60112

Descriptive Properties	Value	Comments
Ball Pressure Test, 75°C +/- 2°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China