

## SABIC Innovative Plastics EXTEM UH1016 TPI Blend (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyimide, Thermoplastic

**Material Notes:**

High heat amorphous TPI Blend, Chemical Resistant, High Flow

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-EXTEM-UH1016-TPI-Blend-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-EXTEM-UH1016-TPI-Blend-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 g/cc	1.37 g/cc	ASTM D792
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.60 % @Time 173000 sec	0.60 % @Time 48.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0080 - 0.010 cm/cm @Thickness 3.20 mm	0.0080 - 0.010 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	12 g/10 min @Load 6.60 kg, Temperature 400 °C	12 g/10 min @Load 14.6 lb, Temperature 752 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	105 MPa	15200 psi	5 mm/min; ISO 527
	110 MPa	16000 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	112 MPa	16200 psi	5 mm/min; ISO 527
	120 MPa	17400 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	10 %	10 %	Type I, 5 mm/min; ASTM D638
	17 %	17 %	5 mm/min; ISO 527
Elongation at Yield	9.0 %	9.0 %	Type I, 5 mm/min; ASTM D638
	9.0 %	9.0 %	5 mm/min; ISO 527
Tensile Modulus	3.50 GPa	508 ksi	1 mm/min; ISO 527
	3.80 GPa	551 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	155 MPa	22500 psi	2 mm/min; ISO 178
			1.3 mm/min, 50 mm span; ASTM

Mechanical Properties	175 MPa Metric	25400 psi English	D790 Comments
Flexural Modulus	3.00 GPa	435 ksi	2 mm/min; ISO 178
	3.52 GPa	511 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.600 J/cm	1.12 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	9.00 kJ/m <sup>2</sup>	4.28 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Charpy Impact, Notched	2.20 J/cm <sup>2</sup>	10.5 ft-lb/in <sup>2</sup>	ISO 179/2C

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	46.0 µm/m-°C	25.6 µin/in-°F	ASTM E 831
	@Temperature 23.0 - 150 °C	@Temperature 73.4 - 302 °F	
CTE, linear, Transverse to Flow	47.0 µm/m-°C	26.1 µin/in-°F	ASTM E 831
	@Temperature 23.0 - 150 °C	@Temperature 73.4 - 302 °F	
Deflection Temperature at 0.46 MPa (66 psi)	263 °C	505 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	231 °C	448 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	240 °C	464 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	257 °C	495 °F	Rate B/50; ASTM D1525
	261 °C	502 °F	Rate B/50; ISO 306
	263 °C	505 °F	Rate B/120; ISO 306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China