

SABIC Innovative Plastics LNP FARADEx DS0036IR PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* FARADEx* DS0036IR is a compound based on Polycarbonate resin containing Stainless Steel Fiber, Flame Retardant. Added features include: Improved Paintability, Non-Brominated & Non-Chlorinated Flame Retardant, EMI/RFI- Shielding, High Impact

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-FARADEx-DS0036IR-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	59.0 MPa	8560 psi	5 mm/min; ISO 527
Elongation at Yield	4.2 %	4.2 %	5 mm/min; ISO 527
Tensile Modulus	2.30 GPa	334 ksi	1 mm/min; ISO 527
Flexural Yield Strength	86.0 MPa	12500 psi	2 mm/min; ISO 178
Flexural Modulus	2.70 GPa	392 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	14.0 kJ/m ²	6.66 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	70.0 kJ/m ²	33.3 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	135 °C	275 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
Flammability, UL94	V-2 @Thickness 1.50 - 1.65 mm	V-2 @Thickness 0.0591 - 0.0650 in	UL 94

Electrical Properties	Metric	English	Comments
Shielding Effectiveness	40 - 55 dB @Thickness 3.00 mm	40 - 55 dB @Thickness 0.118 in	SABIC Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China