

## SABIC Innovative Plastics LNP FARADEx MS002 PP

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

LNP\* FARADEx\* MS002 is a compound based on Polypropylene resin containing 10% Stainless Steel. Added features of this material include: Electrically Conductive, EMI/RFI Shielding.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-FARADEx-MS002-PP.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-FARADEx-MS002-PP.php)

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in <sup>3</sup>	ASTM D792
	0.970 g/cc	0.0350 lb/in <sup>3</sup>	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	15.0 MPa	2180 psi	ISO 527
Tensile Strength, Yield	19.0 MPa	2760 psi	ISO 527
Elongation at Break	70 %	70 %	ISO 527
Elongation at Yield	6.1 %	6.1 %	ISO 527
Tensile Modulus	1.20 GPa	174 ksi	1 mm/min; ISO 527
Flexural Strength	31.0 MPa	4500 psi	ISO 178
Flexural Modulus	1.40 GPa	203 ksi	ISO 178
Izod Impact, Notched (ISO)	25.0 kJ/m <sup>2</sup>	11.9 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	100 kJ/m <sup>2</sup>	47.6 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	116 µm/m-°C	64.4 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	156 µm/m-°C	86.7 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 1.8 MPa (264 psi)	56.0 °C	133 °F	Flatw 80*10*4 sp=64mm; ISO 75/ Af

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Surface Resistance Electrical Properties	10 - 1000 ohm Metric	10 - 1000 ohm English	ASTM D257 Comments
Shielding Effectiveness	40 - 55 dB @Thickness 3.00 mm	40 - 55 dB @Thickness 0.118 in	SABIC Method

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China