

SABIC Innovative Plastics LNP LUBRICOMP GX07409H PSU

Category : Polymer , Thermoplastic , Polysulfone (PSU)

Material Notes:

LNP* LUBRICOMP* GX07409H is a compound based on PSU resin containing proprietary fillers. Added features of this grade include: Wear Resistant, Healthcare.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-GX07409H-PSU.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0051 - 0.0071 cm/cm @Time 86400 sec	0.0051 - 0.0071 in/in @Time 24.0 hour	ASTM D955
Linear Mold Shrinkage, Transverse	0.0063 - 0.0083 cm/cm @Time 86400 sec	0.0063 - 0.0083 in/in @Time 24.0 hour	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	48.0 MPa	6960 psi	5 mm/min; ISO 527
Tensile Strength, Yield	68.0 MPa	9860 psi	5 mm/min; ISO 527
Elongation at Break	9.3 %	9.3 %	5 mm/min; ISO 527
Elongation at Yield	5.8 %	5.8 %	5 mm/min; ISO 527
Tensile Modulus	2.52 GPa	365 ksi	1 mm/min; ISO 527
Flexural Yield Strength	88.0 MPa	12800 psi	2 mm/min; ISO 178
Flexural Modulus	2.64 GPa	383 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	9.00 kJ/m ²	4.28 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	219 kJ/m ²	104 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	167 °C	333 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China