

## SABIC Innovative Plastics LNP LUBRILOY DF2049 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

LNP\* Lubriloy\* DF2049 is a compound based on Polycarbonate resin containing Glass Fiber, Proprietary Lubricant. Added features of this material include: Internally Lubricated, Flame Retardant.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-LUBRILOY-DF2049-PC-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRILOY-DF2049-PC-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage, Flow	0.0020 cm/cm @Time 86400 sec	0.0020 in/in @Time 24.0 hour	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Tensile Modulus	7.79 GPa	1130 ksi	50 mm/min; ASTM D638
Flexural Strength	120 MPa	17400 psi	ASTM D790
Flexural Modulus	5.65 GPa	819 ksi	ASTM D790
Izod Impact, Notched	1.12 J/cm	2.10 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.85 J/cm	11.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	140 °C @Thickness 3.20 mm	284 °F @Thickness 0.126 in	unannealed; ASTM D648

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China