

SABIC Innovative Plastics LNP STAT-KON DD000CEX PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP STAT-KON* DD000CEX is a compound based on Polycarbonate resin containing Carbon. Added features of this material include: Clean Compounding System. Easy Molding, Electrically Conductive.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-DD000CEX-PC.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm @Time 86400 sec	0.0060 - 0.0080 in/in @Time 24.0 hour	ASTM D955
Linear Mold Shrinkage, Transverse	0.0060 - 0.0080 cm/cm @Time 86400 sec	0.0060 - 0.0080 in/in @Time 24.0 hour	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	53.0 MPa	7690 psi	ASTM D638
Elongation at Break	7.4 %	7.4 %	ASTM D638
Tensile Modulus	2.48 GPa	360 ksi	50 mm/min; ASTM D638
Flexural Strength	96.0 MPa	13900 psi	ASTM D790
Flexural Modulus	2.72 GPa	395 ksi	ASTM D790
Izod Impact, Notched	0.480 J/cm	0.899 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.94 J/cm	13.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	63.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	35.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	ASTM E 831
CTE, linear, Transverse to Flow	63.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	35.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	137 $\text{Å}^\circ\text{C}$ @Thickness 3.20 mm	279 $\text{Å}^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	10000 - 1.00e+7 ohm	10000 - 1.00e+7 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China