

## SABIC Innovative Plastics LNP STAT-KON DE002 PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

LNP\* STAT-KON\* DE002 is a Polycarbonate base resin containing 10% Carbon Fiber. Added feature of this grade is: Electrically Conductive.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-STAT-KON-DE002-PC.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-DE002-PC.php)

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in <sup>3</sup>	ASTM D792
	1.29 g/cc	0.0466 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.0800 %	0.0800 %	50% RH, 24 hrs; ASTM D570
	0.0800 %	0.0800 %	23 <sup>o</sup> C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	97.0 MPa	14100 psi	Type I, 5 mm/min; ASTM D638
	97.0 MPa	14100 psi	5 mm/min; ISO 527
Elongation at Break	7.2 %	7.2 %	5 mm/min; ISO 527
	7.5 %	7.5 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	10.34 GPa	1500 ksi	1 mm/min; ISO 527
	11.14 GPa	1616 ksi	50 mm/min; ASTM D638
Flexural Strength	149 MPa	21600 psi	ISO 178
	158 MPa	22900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	7.44 GPa	1080 ksi	2 mm/min; ISO 178
	7.46 GPa	1080 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Unnotched	0.0900 J/cm	0.169 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	5.00 kJ/m <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A

Mechanical Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	25.7 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -30.0 - 30.0 $\text{Å}^\circ\text{C}$	14.3 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -22.0 - 86.0 $\text{Å}^\circ\text{F}$	ASTM D696
CTE, linear, Transverse to Flow	57.9 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -30.0 - 30.0 $\text{Å}^\circ\text{C}$	32.2 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -22.0 - 86.0 $\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	145 $\text{Å}^\circ\text{C}$	293 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	146 $\text{Å}^\circ\text{C}$ @Thickness 3.20 mm	295 $\text{Å}^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	142 $\text{Å}^\circ\text{C}$	288 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af
	141 $\text{Å}^\circ\text{C}$ @Thickness 3.20 mm	286 $\text{Å}^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648

  

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.0 - 6.0 ohm-cm	4.0 - 6.0 ohm-cm	ASTM D257
Surface Resistance	3.0 - 5.0 ohm	3.0 - 5.0 ohm	ASTM D257

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China