

SABIC Innovative Plastics LNP STAT-KON DX05301C PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Low Ionic, Low Outgassing, Low LPC and ESD safe Polycarbonate compound suitable for Semiconductor and Hard Disk Drive (HDD) application. Added features of this material include: Clean Compounding System. This product is also known as STAT-KON PDX-D-05301 CCS.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-DX05301C-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792
Density	1.22 g/cc	0.0441 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0060 cm/cm	0.0060 in/in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	SABIC Method
Melt Flow	22.6 g/10 min @Load 5.00 kg, Temperature 300 Â°C	22.6 g/10 min @Load 11.0 lb, Temperature 572 Â°F	ASTM D1238
Melt Index of Compound	22 g/10 min @Load 5.00 kg, Temperature 300 Â°C	22 g/10 min @Load 11.0 lb, Temperature 572 Â°F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	56.0 MPa	8120 psi	5 mm/min; ISO 527
	60.0 MPa	8700 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	48.0 MPa	6960 psi	Type I, 5 mm/min; ASTM D638
	56.0 MPa	8120 psi	5 mm/min; ISO 527
Elongation at Break	1.5 %	1.5 %	5 mm/min; ISO 527
	9.9 %	9.9 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	1.5 %	1.5 %	5 mm/min; ISO 527
	5.3 %	5.3 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	2.49 GPa	361 ksi	1 mm/min; ISO 527
	2.59 GPa	376 ksi	5 mm/min; ASTM D638

Flexural Yield Strength Mechanical Properties	77.0 MPa Metric	11200 psi English	2 mm/min; ISO 178 Comments
	95.0 MPa	13800 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.28 GPa	331 ksi	1.3 mm/min, 50 mm span; ASTM D790
	2.48 GPa	360 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.540 J/cm	1.01 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	80*10*4; ISO 180/1A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	131 Â°C	268 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	132 Â°C	270 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	146 Â°C	295 Â°F	Rate B/120; ISO 306

Electrical Properties	Metric	English	Comments
Volume Resistivity	1e+05 - 1.00e+8 ohm-cm	1e+05 - 1.00e+8 ohm-cm	ASTM D257
Surface Resistance	1e+05 - 1.00e+8 ohm	1e+05 - 1.00e+8 ohm	ASTM D257
Static Decay	0.10 sec	0.10 sec	5000V to <50V; FTMS101B

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China