

SABIC Innovative Plastics LNP STAT-KON EEF42 PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

LNP STAT-KON* EEF42 is a compound based on Polyetherimide resin containing Carbon Fiber, Glass Fiber. Added features of this material include: Electrically Conductive.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-EEF42-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0010 - 0.0020 cm/cm @Time 86400 sec	0.0010 - 0.0020 in/in @Time 24.0 hour	ASTM D955
Linear Mold Shrinkage, Transverse	0.0030 - 0.0040 cm/cm @Time 86400 sec	0.0030 - 0.0040 in/in @Time 24.0 hour	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	194 MPa	28100 psi	ASTM D638
Elongation at Break	1.7 %	1.7 %	ASTM D638
Tensile Modulus	15.85 GPa	2299 ksi	50 mm/min; ASTM D638
Flexural Strength	275 MPa	39900 psi	ASTM D790
Flexural Modulus	15.85 GPa	2299 ksi	ASTM D790
Izod Impact, Notched	0.710 J/cm	1.33 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.07 J/cm	9.50 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	33.4 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$ @Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	18.6 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$ @Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	ASTM E 831
CTE, linear, Transverse to Flow	23.3 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$ @Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	12.9 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$ @Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	ASTM E 831
Deflection Temperature at 1.8 MPa (264 psi)	211 $\text{Å}^\circ\text{C}$ @Thickness 3.20 mm	412 $\text{Å}^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 - 1.00e+11 ohm-cm	1.00e+10 - 1.00e+11 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China