

SABIC Innovative Plastics LNP THERMOCOMP AX08306 ABS

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

LNP* THERMOCOMP* AX08306 is a compound based on ABS resin containing Proprietary Filler(s). Added feature of this grade is: Platable.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-AX08306-ABS.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ASTM D792
	1.17 g/cc	0.0423 lb/in ³	ISO 1183
Moisture Absorption	0.220 %	0.220 %	50% RH, 24 hrs; ASTM D570
	0.320 %	0.320 %	23 ^o C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0050 cm/cm	0.0050 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	33.0 MPa	4790 psi	ISO 527
	34.0 MPa	4930 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	36.0 MPa	5220 psi	ISO 527
	37.0 MPa	5370 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	6.9 %	6.9 %	Type I, 5 mm/min; ASTM D638
	7.5 %	7.5 %	ISO 527
Elongation at Yield	64.1 %	64.1 %	Flexural Strain, break, 2 mm/min; ISO 178
	1.8 %	1.8 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	3.18 GPa	461 ksi	5 mm/min; ASTM D638
Flexural Strength	64.0 MPa	9280 psi	ISO 178
	92.0 MPa	13300 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	3.01 GPa	437 ksi	ISO 178

Mechanical Properties	Metric ^{Pa}	English	Comments 1.3 mm/min, 50 mm span; ASTM D750
Izod Impact, Notched	0.260 J/cm	0.487 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.88 J/cm	5.40 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	3.00 kJ/m ²	1.43 ft-lb/in ²	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	22.0 kJ/m ²	10.5 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	87.0 Â°C	189 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	86.0 Â°C	187 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.75	2.75	ASTM D150
	@Frequency 1.00e+9 Hz	@Frequency 1.00e+9 Hz	
Dissipation Factor	0.0024	0.0024	ASTM D150
	@Frequency 1.00e+9 Hz	@Frequency 1.00e+9 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China