

**SABIC Innovative Plastics LNP THERMOCOMP BFL2200 PC (Asia Pacific)**

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

design for black light frame application as high flow PC, V-2, high reflection grade.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-THERMOCOMP-BFL2200-PC-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-BFL2200-PC-Asia-Pacific.php)

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	61.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	33.9 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
	68.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	37.8 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
CTE, linear, Transverse to Flow	68.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	37.8 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
	69.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	38.3 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China