

## SABIC Innovative Plastics LNP THERMOCOMP KF006XXC Acetal Copolymer (Asia Pacific)

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, 30% Glass Fiber Reinforced

### Material Notes:

LNP\* Thermocomp\* KF006XXC is a compound based on Acetal Copolymer resin containing Glass Fiber.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-THERMOCOMP-KF006XXC-Acetal-Copolymer-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-KF006XXC-Acetal-Copolymer-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Density	1.64 g/cc	0.0592 lb/in <sup>3</sup>	ASTM D792
	1.64 g/cc	0.0592 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.200 %	0.200 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0049 cm/cm	0.0049 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0050 cm/cm	0.0050 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.016 cm/cm	0.016 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.016 cm/cm	0.016 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	115 MPa	16700 psi	ASTM D638
	121 MPa	17500 psi	ISO 527
Tensile Strength, Yield	115 MPa	16700 psi	ASTM D638
	121 MPa	17500 psi	ISO 527
Elongation at Break	2.0 %	2.0 %	ASTM D638
	2.1 %	2.1 %	ISO 527
Elongation at Yield	2.0 %	2.0 %	ASTM D638
	2.1 %	2.1 %	ISO 527
Tensile Modulus	10.35 GPa	1501 ksi	1 mm/min; ISO 527

Mechanical Properties	11.03 GPa Metric	1600 ksi English	50 mm/min; ASTM D638 Comments
Flexural Strength	172 MPa	24900 psi	ASTM D790
	176 MPa	25500 psi	ISO 178
Flexural Modulus	9.00 GPa	1310 ksi	ISO 178
	9.65 GPa	1400 ksi	ASTM D790
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.40 J/cm	12.0 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	7.00 kJ/m <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	41.0 kJ/m <sup>2</sup>	19.5 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U
Dart Drop, Total Energy	8.00 J	5.90 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	3.00 J	2.21 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	82.0 Åµm/m-Å°C	45.6 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	82.8 Åµm/m-Å°C	46.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	36.0 Åµm/m-Å°C	20.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	37.0 Åµm/m-Å°C	20.6 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	164 Å°C	327 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	162 Å°C	324 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	161 Å°C	322 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	162 Å°C	324 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**