

SABIC Innovative Plastics LNP THERMOCOMP Lexan_LGK5030 PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Thermocomp* Lexan_LGN5030 compound is a glass reinforced. Flame retardant.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-LexanLGK5030-PC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.61 g/cc	1.61 g/cc	ASTM D792
Water Absorption	0.14 %	0.14 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.00050 - 0.0025 cm/cm	0.00050 - 0.0025 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	142 MPa	20600 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	Type I, 50 mm/min; ASTM D638
Flexural Strength	186 MPa	27000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	10.7 GPa	1550 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.22 J/cm	2.29 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	21.6 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$	12.0 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
	@Temperature -30.0 - 30.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 86.0 $\text{Å}^\circ\text{F}$	
CTE, linear, Transverse to Flow	39.6 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$	22.0 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
	@Temperature -30.0 - 30.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 86.0 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	143 $\text{Å}^\circ\text{C}$	289 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Thermal Properties	V-1 Metric	V-1 English	Comments
	@Thickness 1.47 mm	@Thickness 0.0579 in	
	V-0	V-0	UL 94
	@Thickness 2.79 mm	@Thickness 0.110 in	
	5VA	5VA	UL 94
	@Thickness 3.60 mm	@Thickness 0.142 in	

Electrical Properties	Metric	English	Comments
Dielectric Strength	16.3 kV/mm	414 kV/in	in oil; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China