

SABIC Innovative Plastics LNP VERTON RV00AESS PA 66 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

LNP* VERTON* RV00AESS is a compound based on PA 66 resin containing Long Glass Fiber. Added features include; Easy Molding, Heat Stabilized.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-VERTON-RV00AESS-PA-66-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.60 g/cc	0.0578 lb/in ³	ISO 1183
Water Absorption	0.90 %	0.90 %	ISO 62-1
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	276 MPa	40000 psi	5 mm/min; ISO 527
Tensile Strength, Yield	276 MPa	40000 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
	3.0 %	3.0 %	
Elongation at Yield	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	17.8 GPa	2580 ksi	1 mm/min; ISO 527
Flexural Yield Strength	366 MPa	53100 psi	2 mm/min; ISO 178
Flexural Modulus	15.0 GPa	2180 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	45.0 kJ/m ²	21.4 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	90.0 kJ/m ²	42.8 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa	259 °C	498 °F	

(56 psi) Thermal Properties	Metric	English	Flatw 80*10*4 sp=64mm; ISO 75/Bf Comments
Deflection Temperature at 1.8 MPa (264 psi)	256 Â°C	493 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
UL RTI, Electrical	105 Â°C	221 Â°F	UL 746B
UL RTI, Mechanical with Impact	110 Â°C	230 Â°F	UL 746B
UL RTI, Mechanical without Impact	110 Â°C	230 Â°F	UL 746B
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	UL 94

Electrical Properties	Metric	English	Comments
Hot Wire Ignition, HWI	0.00 - 2.0 sec	0.00 - 2.0 sec	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China