

SABIC Innovative Plastics Lexan® EXL1810T PC Copolymer (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan® EXL1810T polycarbonate (PC) siloxane copolymer resin is a transparent injection molding grade. This resin offers cold temperature (0 °C) ductility in combination with very high flow characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC resin. Lexan EXL1810T resin is a general purpose product available in transparent and opaque colors and is an excellent candidate for a broad range of applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-EXL1810T-PC-Copolymer-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183
Moisture Absorption	0.0900 %	0.0900 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.12 %	0.12 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	35 g/10 min @Load 1.20 kg, Temperature 300 °C	35 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	33 g/10 min @Load 1.20 kg, Temperature 300 °C	33 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	90	90	ISO 2039-2
Tensile Strength at Break	56.0 MPa	8120 psi	50 mm/min; ISO 527
	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	59.0 MPa	8560 psi	Type I, 50 mm/min; ASTM D638
	59.0 MPa	8560 psi	50 mm/min; ISO 527
Elongation at Break	118.6 %	118.6 %	50 mm/min; ISO 527

Mechanical Properties	118.9 % Metric	118.9 % English	Type I, 50 mm/min; ASTM D638 Comments
Elongation at Yield	5.4 %	5.4 %	50 mm/min; ISO 527
	5.8 %	5.8 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.36 GPa	342 ksi	50 mm/min; ASTM D638
	2.40 GPa	348 ksi	1 mm/min; ISO 527
Flexural Yield Strength	92.0 MPa	13300 psi	2 mm/min; ISO 178
	99.0 MPa	14400 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.25 GPa	326 ksi	2 mm/min; ISO 178
	2.35 GPa	341 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.02 J/cm	13.2 ft-lb/in	ASTM D256
	2.20 J/cm	4.12 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	60.0 kJ/m ²	28.6 ft-lb/in ²	80*10*3; ISO 180/1A
	30.0 kJ/m ²	14.3 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	6.50 J/cm ²	30.9 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	4.00 J/cm ²	19.0 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	79.0 J	58.3 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
	65.0 μm/m-°C	36.1 μin/in-°F	

Thermal Properties	Metric	English	Comments
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	65.0 µm/m-°C	36.1 µin/in-°F	
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	ISO 11359-2
CTE, linear, Transverse to Flow	74.0 µm/m-°C	41.1 µin/in-°F	
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	ASTM E 831
	74.0 µm/m-°C	41.1 µin/in-°F	
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	ISO 11359-2
Deflection Temperature at 1.8 MPa (264 psi)	117 °C	243 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	120 °C	248 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	137 °C	279 °F	Rate B/50; ISO 306
	138 °C	280 °F	Rate A/50; ASTM D1525
	140 °C	284 °F	Rate B/120; ISO 306
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746B
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	UL 94
Glow Wire Test	825 °C	1520 °F	IEC 60695-2-13
	850 °C	1560 °F	IEC 60695-2-13
	960 °C	1760 °F	
	@Thickness 3.00 mm	@Thickness 0.118 in	IEC 60695-2-12

Optical Properties	Metric	English	Comments
Haze	3.0 %	3.0 %	
	@Thickness 2.54 mm	@Thickness 0.100 in	ASTM D1003
Transmission, Visible	82 %	82 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	$\geq 1.00\text{e}+15$ ohm-cm Metric	$\geq 1.00\text{e}+15$ ohm-cm English	ASTM D257 Comments
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	ASTM D257

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASS	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China