

SABIC Innovative Plastics Lexan® FXD103 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

FXD103 is a Light Diffusion effect, part of the VisualFX family. These effects have been developed to meet increasing Aesthetic demands in the Marketplace. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXD103-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D 792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.15 %	0.15 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 % @Temperature 23.0 °C	0.35 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on tensile bar; SABIC Method
	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	6.0 g/10 min @Load 1.20 kg, Temperature 300 °C	6.0 g/10 min @Load 2.65 lb, Temperature 572 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	7.0 g/10 min @Load 1.20 kg, Temperature 300 °C	7.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	66.0 MPa	9570 psi	Type I, 50 mm/min; ASTM D 638
	70.0 MPa	10200 psi	50 mm/min; ISO 527
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D 638
	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	110 %	110 %	Type I, 50 mm/min; ASTM D 638
	120 %	120 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D 638

Mechanical Properties	Metric	English	Comments
Tensile Modulus	2.34 GPa	339 ksi	5 mm/min; ASTM D 638
	2.35 GPa	341 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	93.0 MPa	13500 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	1.44 J/cm	2.70 ft-lb/in	ASTM D 256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	9.08 J/cm	17.0 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched	32.04 J/cm	60.02 ft-lb/in	ASTM D 4812
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	12.0 kJ/m ²	5.71 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	65.0 kJ/m ²	30.9 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	70.0 kJ/m ²	33.3 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	80*10*3; ISO 180/1U
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	1.50 J/cm ²	7.14 ft-lb/in ²	V-notch Edgew 80*10*3 sp=62mm;

Charpy Impact, Notched Mechanical Properties	@Temperature -30.0 °C Metric	@Temperature -22.0 °F English	ISO 179/1eA Comments
	7.50 J/cm ²	35.7 ft-lb/in ²	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	68.0 J	50.2 ft-lb	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	71.7 µm/m-°C	39.8 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
CTE, linear, Transverse to Flow	71.0 µm/m-°C	39.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	72.7 µm/m-°C	40.4 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
Deflection Temperature at 0.46 MPa (66 psi)	138 °C	280 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	138 °C	280 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D 648
Deflection Temperature at 1.8 MPa (264 psi)	127 °C	261 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	132 °C	270 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D 648
Vicat Softening Point	144 °C	291 °F	Rate B/50; ISO 306
	145 °C	293 °F	Rate B/120; ISO 306
	154 °C	309 °F	Rate B/50; ASTM D 1525
Flammability, UL94	HB	HB	UL 94 by SABIC-IP
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Descriptive Properties	Value	Comments
Ball Pressure Test, 75°C +/- 2°C	Pass	IEC 60695-10-2

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China