

SABIC Innovative Plastics Lexan® FXM941A PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

PC in special effects colors. Metallic and pearlescent additives. Color package may affect performance.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXM941A-PC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10.2 g/10 min @Load 1.20 kg, Temperature 300 °C	10.2 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	57.0 MPa	8270 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	61.0 MPa	8850 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	95 %	95 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.30 GPa	334 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	95.0 MPa	13800 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.39 GPa	347 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	ASTM D256
Dart Drop, Total Energy	59.0 J @Temperature 23.0 °C	43.5 ft-lb @Temperature 73.4 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	137 °C @Thickness 3.20 mm	279 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	126 °C @Thickness 3.20 mm	259 °F @Thickness 0.126 in	unannealed; ASTM D648

Thermal Properties	Metric	English	Comments
UL RTI, Mechanical with Impact	80.0 °C	176 °F	UL 746B
UL RTI, Mechanical without Impact	80.0 °C	176 °F	UL 746B
Flammability, UL94	V-2	V-2	UL 94
	@Thickness 1.52 mm	@Thickness 0.0598 in	
	V-0	V-0	UL 94
	@Thickness 3.04 mm	@Thickness 0.120 in	

Electrical Properties	Metric	English	Comments
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	Tungsten; ASTM D495
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China