

SABIC Innovative Plastics Lexan® HP3AEU PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan HP3AEU resin is a medium flow polycarbonate with mold release designed for medical devices and pharmaceutical applications. It is assessed with biocompatible ISO10993 (or USP Class VI) and is EtO and steam sterilizable. It is under SABIC Innovative Plastics healthcare management of change policy.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HP3AEU-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	14 g/10 min @Load 1.20 kg, Temperature 300 °C	14 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	12 g/10 min @Load 1.20 kg, Temperature 300 °C	12 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	95.0 MPa	13800 psi	ISO 2039-1
Tensile Strength at Break	68.0 MPa	9860 psi	Type I, 50 mm/min; ASTM D638
	70.0 MPa	10200 psi	50 mm/min; ISO 527
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	110 %	110 %	50 mm/min; ISO 527
	130 %	130 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
			Type 1, 50 mm/min; ASTM D638
Tensile Modulus	2.35 GPa	341 ksi	1 mm/min; ISO 527
	2.37 GPa	344 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
Izod Impact, Notched	8.00 J/cm	15.0 ft-lb/in	ASTM D256
	1.00 J/cm	1.87 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	70.0 kJ/m ²	33.3 ft-lb/in ²	80*10*3; ISO 180/1A
	10.0 kJ/m ²	4.76 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	3.50 J/cm ²	16.7 ft-lb/in ²	ISO 179/2C
	7.00 J/cm ²	33.3 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.50 J/cm ²	7.14 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	63.0 J	46.5 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Taber Abrasion, mg/1000 Cycles	10	10	CS-17, 1 kg; SABIC Method

Thermal Properties	Metric	English	Comments
	68.4 µm/m-°C	38.0 µin/in-°F	
CTE, linear, Parallel to Flow			ASTM E 831

Thermal Properties	@Temperature -40.0 - Metric 95.0 °C	@Temperature -40.0 - English 203 °F	Comments
	70.0 µm/m-°C	38.9 µin/in-°F	
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	ISO 11359-2
CTE, linear, Transverse to Flow	68.4 µm/m-°C	38.0 µin/in-°F	
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	ASTM E 831
	70.0 µm/m-°C	38.9 µin/in-°F	
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	ISO 11359-2
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ISO 8302
Hot Ball Pressure Test	<= 140 °C	<= 284 °F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	136 °C	277 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	125 °C	257 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	132 °C	270 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	141 °C	286 °F	Rate B/50; ASTM D1525
	141 °C	286 °F	Rate B/50; ISO 306
	142 °C	288 °F	Rate B/120; ISO 306
	153 °C	307 °F	Rate A/50; ISO 306
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical with Impact	125 °C	257 °F	UL 746B
UL RTI, Mechanical without Impact	125 °C	257 °F	UL 746B
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	UL 94
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	UL 94
Oxygen Index	25 %	25 %	ISO 4589
Glow Wire Test	850 °C	1560 °F	
	@Thickness 1.00 mm	@Thickness 0.0394 in	IEC 60695-2-12

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ISO 489
Haze	<= 0.80 % @Thickness 2.54 mm	<= 0.80 % @Thickness 0.100 in	ASTM D1003
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	2.7 @Frequency 1.00e+6 Hz	2.7 @Frequency 1.00e+6 Hz	IEC 60250
	2.7 @Frequency 50.0 - 60.0 Hz	2.7 @Frequency 50.0 - 60.0 Hz	IEC 60250
Dielectric Strength	15.0 kV/mm @Thickness 1.00 mm	381 kV/in @Thickness 0.0394 in	short time; IEC 60243-1
	17.0 kV/mm @Thickness 3.20 mm	432 kV/in @Thickness 0.126 in	in oil; IEC 60243-1
Dissipation Factor	0.0010 @Frequency 50.0 - 60.0 Hz	0.0010 @Frequency 50.0 - 60.0 Hz	IEC 60250
	0.010 @Frequency 1.00e+6 Hz	0.010 @Frequency 1.00e+6 Hz	IEC 60250

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China