

## SABIC Innovative Plastics Lexan® SFX123RU PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

SFX123RU is a transparent SecurFX grade with improved flow, mold release and UV stabilizer. This grade is for security applications and contains proprietary authentication technology. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-SFX123RU-PC-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-SFX123RU-PC-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D 792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	17.5 g/10 min @Load 1.20 kg, Temperature 300 °C	17.5 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	68.0 MPa	9860 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D 638
Elongation at Break	125 %	125 %	Type I, 50 mm/min; ASTM D 638
Elongation at Yield	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D 638
Flexural Yield Strength	96.0 MPa	13900 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	6.94 J/cm @Temperature 23.0 °C	13.0 ft-lb/in @Temperature 73.4 °F	ASTM D 256
Izod Impact, Unnotched	32.04 J/cm @Temperature 23.0 °C	60.02 ft-lb/in @Temperature 73.4 °F	ASTM D 4812
Impact Test	62.0 J @Temperature 23.0 °C	45.7 ft-lb @Temperature 73.4 °F	Instrumented Impact Total Energy; ASTM D 3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa	137 °C	279 °F	unannealed; ASTM D 648

<small>(56 psi)</small> Thermal Properties	@Thickness 6.40 mm Metric	@Thickness 0.252 in English	Comments
	137 °C	279 °F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	126 °C	259 °F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
	129 °C	264 °F	unannealed; ASTM D 648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	154 °C	309 °F	Rate B/50; ASTM D 1525

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China