

## SABIC Innovative Plastics Lexan® SLX1482T PC Copolymer (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

Medium viscosity PC Copolymer, enhanced UV stabilization. Transparent and tinted colors. Higher mold release content than SLX1432T. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-SLX1482T-PC-Copolymer-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-SLX1482T-PC-Copolymer-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D 792
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.12 % @Time 86400 sec	0.12 % @Time 24.0 hour	ASTM D 570
Moisture Absorption at Equilibrium	0.17 %	0.17 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.25 % @Temperature 23.0 °C	0.25 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	9.0 g/10 min @Load 1.20 kg, Temperature 300 °C	9.0 g/10 min @Load 2.65 lb, Temperature 572 °F	[cm <sup>3</sup> /10 min] Melt Volume Rate; ISO 1133
	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	69.0 MPa	10000 psi	50 mm/min; ISO 527
	72.0 MPa	10400 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527
	67.0 MPa	9720 psi	Type I, 50 mm/min; ASTM D 638

Elongation at Break Mechanical Properties	110 % Metric	110 % English	Type I, 50 mm/min; ASTM D 638 Comments
	110 %	110 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D 638
	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.55 GPa	370 ksi	50 mm/min; ASTM D 638
	2.55 GPa	370 ksi	1 mm/min; ISO 527
Flexural Yield Strength	105 MPa	15200 psi	1.3 mm/min, 50 mm span; ASTM D 790
	105 MPa	15200 psi	2 mm/min; ISO 178
Flexural Modulus	2.50 GPa	363 ksi	1.3 mm/min, 50 mm span; ASTM D 790
	2.50 GPa	363 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.980 J/cm @Temperature -30.0 °C	1.84 ft-lb/in @Temperature -22.0 °F	ASTM D 256
	7.00 J/cm @Temperature 23.0 °C	13.1 ft-lb/in @Temperature 73.4 °F	ASTM D 256
Izod Impact, Unnotched	26.0 J/cm @Temperature 23.0 °C	48.7 ft-lb/in @Temperature 73.4 °F	ASTM D 4812
Izod Impact, Notched (ISO)	10.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	4.76 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*3; ISO 180/1A
	25.0 kJ/m <sup>2</sup> @Temperature 23.0 °C	11.9 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	80*10*3; ISO 180/1U
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eU
Charpy Impact, Notched	1.50 J/cm <sup>2</sup> @Temperature -30.0 °C	7.14 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	3.00 J/cm <sup>2</sup> @Temperature 23.0 °C	14.3 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
Impact Test	77.0 J	56.8 ft-lb	Instrumented Impact Total Energy;

Mechanical Properties	@Temperature 23.0 °C Metric	@Temperature 73.4 °F English	ASTM D 3763 Comments
	85.0 J	62.7 ft-lb	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	66.6 µm/m-°C	37.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	66.6 µm/m-°C	37.0 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	64.8 µm/m-°C	36.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	64.8 µm/m-°C	36.0 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	130 °C	266 °F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	116 °C	241 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	118 °C	244 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D 648
Vicat Softening Point	135 °C	275 °F	Rate B/50; ASTM D 1525
	135 °C	275 °F	Rate B/50; ISO 306
	137 °C	279 °F	Rate B/120; ISO 306
Flammability, UL94	HB	HB	UL 94
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.59	1.59	ASTM D 542

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**