

SABIC Innovative Plastics Lexan® SLX2432T PC Copolymer (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Medium viscosity PC copolymer with enhanced UV stabilization and added release agent. V2 rated. Available in transparent and tinted colors.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-SLX2432T-PC-Copolymer-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Water Absorption	0.12 % @Time 86400 sec	0.12 % @Time 24.0 hour	ASTM D570
Moisture Absorption	0.170 %	0.170 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.25 %	0.25 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	9.0 g/10 min @Load 1.20 kg, Temperature 300 °C	9.0 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	69.0 MPa	10000 psi	50 mm/min; ISO 527
	72.0 MPa	10400 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527
	67.0 MPa	9720 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	110 %	110 %	Type I, 50 mm/min; ASTM D638
	110 %	110 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
	6.0 %	6.0 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
Tensile Modulus	2.55 GPa	370 ksi	50 mm/min; ASTM D638
	2.55 GPa	370 ksi	1 mm/min; ISO 527
Flexural Yield Strength	105 MPa	15200 psi	1.3 mm/min, 50 mm span; ASTM D790
	105 MPa	15200 psi	2 mm/min; ISO 178
Flexural Modulus	2.50 GPa	363 ksi	1.3 mm/min, 50 mm span; ASTM D790
	2.50 GPa	363 ksi	2 mm/min; ISO 178
Izod Impact, Notched	7.00 J/cm	13.1 ft-lb/in	ASTM D256
	0.980 J/cm	1.84 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched	26.0 J/cm	48.7 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	25.0 kJ/m ²	11.9 ft-lb/in ²	80*10*3; ISO 180/1A
	10.0 kJ/m ²	4.76 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
Charpy Impact, Notched	3.00 J/cm ²	14.3 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.50 J/cm ²	7.14 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	77.0 J	56.8 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	85.0 J	62.7 ft-lb	ASTM D3763
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	66.6 µm/m-°C	37.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	66.6 µm/m-°C	37.0 µin/in-°F	ISO 11359-2
	@Temperature -40.0 -	@Temperature -40.0 -	

Thermal Properties	40.0 °C Metric	104 °F English	Comments
CTE, linear, Transverse to Flow	64.8 µm/m-°C	36.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	64.8 µm/m-°C	36.0 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	130 °C	266 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	130 °C	266 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	116 °C	241 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	118 °C	244 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	135 °C	275 °F	Rate B/50; ASTM D1525
	135 °C	275 °F	Rate B/50; ISO 306
	137 °C	279 °F	Rate B/120; ISO 306
Flammability, UL94	V-2	V-2	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Oxygen Index	38 %	38 %	ISO 4589
Glow Wire Test	960 °C	1760 °F	IEC 60695-2-12
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.59	1.59	ASTM D542
Haze	0.80 %	0.80 %	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	84 %	84 %	2.54 mm; ASTM D1003

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2
UV-light, water exposure/immersion	F1	UL 746C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China