

**SABIC Innovative Plastics Lexan® XHT4143T PC Copolymer (Asia Pacific)**

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

XHT4143 is a high flow, UV stabilized, high heat polycarbonate copolymer blend with an HDT/Af of 162C.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-XHT4143T-PC-Copolymer-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-XHT4143T-PC-Copolymer-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.21 g/cc	0.0437 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.250 %	0.250 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.33 %	0.33 %	ISO 62
Linear Mold Shrinkage, Flow	0.0060 - 0.0095 cm/cm @Thickness 3.20 mm	0.0060 - 0.0095 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	25 g/10 min @Load 2.16 kg, Temperature 330 °C	25 g/10 min @Load 4.76 lb, Temperature 626 °F	ASTM D1238
Melt Index of Compound	24 g/10 min @Load 2.16 kg, Temperature 330 °C	24 g/10 min @Load 4.76 lb, Temperature 626 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	67.0 MPa	9720 psi	50 mm/min; ISO 527
	69.0 MPa	10000 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	77.0 MPa	11200 psi	Type I, 50 mm/min; ASTM D638
	78.0 MPa	11300 psi	50 mm/min; ISO 527
Elongation at Break	50 %	50 %	Type I, 50 mm/min; ASTM D638
	50 %	50 %	50 mm/min; ISO 527
Elongation at Yield	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D638
	7.0 %	7.0 %	50 mm/min; ISO 527
Tensile Modulus	2.73 GPa	396 ksi	5 mm/min; ASTM D638
	2.75 GPa	399 ksi	1 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
	120 MPa	17400 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.60 GPa	377 ksi	1.3 mm/min, 50 mm span; ASTM D790
	2.60 GPa	377 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.930 J/cm	1.74 ft-lb/in	ASTM D256
	0.760 J/cm	1.42 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	10.0 kJ/m <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	8.00 kJ/m <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.10 J/cm <sup>2</sup>	5.23 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	0.900 J/cm <sup>2</sup>	4.28 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	72.0 J	53.1 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	60.0 µm/m-°C	33.3 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	60.0 µm/m-°C	33.3 µin/in-°F	ASTM E 831

Thermal Properties	Metric @Temperature -40.0 - 40.0 °C	English @Temperature -40.0 - 104 °F	Comments
	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	173 °C	343 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	174 °C	345 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	162 °C	324 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	165 °C	329 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	181 °C	358 °F	Rate B/120; ISO 306
	183 °C	361 °F	Rate B/50; ASTM D1525
	183 °C	361 °F	Rate B/50; ISO 306
Glow Wire Test	850 °C	1560 °F	IEC 60695-2-12
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	960 °C	1760 °F	IEC 60695-2-12
	@Thickness 2.50 mm	@Thickness 0.0984 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.605	1.605	ASTM D542
Transmission, Visible	86 %	86 %	2.54 mm; ASTM D1003

Descriptive Properties	Value	Comments
Ball Pressure Test, 165°C +/- 2°C	PASSES	IEC 60695-10-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China