

SABIC Innovative Plastics NORYL GTX GTX600 PPE+PA6 (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Polyphenylene Ether/PPO

Material Notes:

Pa6 based unfilled GTX

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-GTX-GTX600-PPEPA6-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ASTM D792
Water Absorption	0.60 %	0.60 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	64.0 MPa	9280 psi	SABIC - Japan Method
Elongation at Break	120 %	120 %	SABIC - Japan Method
Flexural Strength	87.0 MPa	12600 psi	ASTM D790
Flexural Modulus	2.05 GPa	297 ksi	ASTM D790
Izod Impact, Notched	6.37 J/cm	11.9 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	75.0 - 85.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	41.7 - 47.2 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	TMA
	@Temperature -30.0 - 30.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 86.0 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	185 $\text{Å}^\circ\text{C}$	365 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China