

SABIC Innovative Plastics NORYL GTX GTX989 PPE+PA (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Polyphenylene Ether/PPO

Material Notes:

NORYL GTX989 is a conductive and high heat material, especially designed for in- and on-line painted bodypanels and fenders in particular. This material combines impact performance with conductivity for electro-static painting in an unique way.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-GTX-GTX989-PPEPA-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Density	1.08 g/cc	0.0390 lb/in ³	ISO 1183
Moisture Absorption	1.20 %	1.20 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	4.2 %	4.2 %	ISO 62
Linear Mold Shrinkage, Flow	0.012 - 0.016 cm/cm @Thickness 3.20 mm	0.012 - 0.016 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	16 g/10 min @Load 5.00 kg, Temperature 280 ^o C	16 g/10 min @Load 11.0 lb, Temperature 536 ^o F	ASTM D1238
Melt Index of Compound	19 g/10 min @Load 5.00 kg, Temperature 280 ^o C	19 g/10 min @Load 11.0 lb, Temperature 536 ^o F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	50 mm/min; ISO 527
	60.0 MPa	8700 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	60.0 MPa	8700 psi	50 mm/min; ISO 527
	65.0 MPa	9430 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	40 %	40 %	50 mm/min; ISO 527
	45 %	45 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	5.0 %	5.0 %	Type I, 50 mm/min; ASTM D638
	5.0 %	5.0 %	50 mm/min; ISO 527
Tensile Modulus	2.30 GPa	334 ksi	1 mm/min; ISO 527

Mechanical Properties	Metric 2.33 GPa	English 337 ksi	Comments 50 mm/min; ASTM D638
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	95.0 MPa	13800 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
	2.45 GPa	355 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	2.40 J/cm	4.50 ft-lb/in	ASTM D256
	1.80 J/cm @Temperature -30.0 Â°C	3.37 ft-lb/in @Temperature -22.0 Â°F	ASTM D256
Izod Impact, Notched (ISO)	22.0 kJ/mÂ²	10.5 ft-lb/inÂ²	80*10*4; ISO 180/1A
	15.0 kJ/mÂ² @Temperature -30.0 Â°C	7.14 ft-lb/inÂ² @Temperature -22.0 Â°F	80*10*4; ISO 180/1A
Charpy Impact, Notched	2.20 J/cmÂ²	10.5 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	1.50 J/cmÂ² @Temperature -30.0 Â°C	7.14 ft-lb/inÂ² @Temperature -22.0 Â°F	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	60.0 J	44.3 ft-lb	ASTM D3763
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	85.0 Âµm/m-Â°C	47.2 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 60.0 Â°C	@Temperature -40.0 - 140 Â°F	
	90.0 Âµm/m-Â°C	50.0 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
CTE, linear, Transverse to Flow	85.0 Âµm/m-Â°C	47.2 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 60.0 Â°C	@Temperature -40.0 - 140 Â°F	
	90.0 Âµm/m-Â°C	50.0 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	185 Â°C	365 Â°F	5.99eW 120*10*4 sp=100mm; ISO 75/Be
	190 Â°C @Thickness 3.20 mm	374 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	180 Â°C	356 Â°F	Rate B/50; ASTM D1525
	195 Â°C	383 Â°F	Rate B/50; ISO 306
	198 Â°C	388 Â°F	Rate B/120; ISO 306

Electrical Properties	Metric	English	Comments
Volume Resistivity	1000 - 10000 ohm-cm	1000 - 10000 ohm-cm	SABIC Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China