

SABIC Innovative Plastics NORYL N802 PPE+HIPS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

PPE/PS 80oC V2 FR high flow

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-N802-PPEHIPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Water Absorption	0.070 % @Time 86400 sec	0.070 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	21 g/10 min @Load 2.16 kg, Temperature 260 Â°C	21 g/10 min @Load 4.76 lb, Temperature 500 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	35.0 MPa	5080 psi	SABIC - Japan Method
Elongation at Break	50 %	50 %	SABIC - Japan Method
Flexural Strength	53.0 MPa	7690 psi	ASTM D790
Flexural Modulus	2.15 GPa	312 ksi	ASTM D790
Izod Impact, Notched	0.780 J/cm	1.46 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	70.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	38.9 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	TMA
Deflection Temperature at 1.8 MPa (264 psi)	80.0 Â°C @Thickness 6.40 mm	176 Â°F @Thickness 0.252 in	unannealed; ASTM D648
Flammability, UL94	V-2 @Thickness 1.40 mm	V-2 @Thickness 0.0551 in	UL 94

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China