

SABIC Innovative Plastics NORYL NC208 PPE+HIPS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-NC208-PPEHIPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Water Absorption	0.060 % @Time 86400 sec	0.060 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm @Thickness 3.20 mm	0.0020 - 0.0040 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	88	88	ASTM D785
Tensile Strength, Yield	78.0 MPa	11300 psi	SABIC - Japan Method
Elongation at Break	4.0 - 6.0 %	4.0 - 6.0 %	SABIC - Japan Method
Flexural Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	4.90 GPa	711 ksi	ASTM D790
Izod Impact, Notched	0.580 J/cm	1.09 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	39.0 - 58.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -30.0 - 30.0 $\text{Å}^\circ\text{C}$	21.7 - 32.2 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -22.0 - 86.0 $\text{Å}^\circ\text{F}$	TMA
Deflection Temperature at 0.46 MPa (66 psi)	132 $\text{Å}^\circ\text{C}$ @Thickness 3.20 mm	270 $\text{Å}^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+8 - 1.00e+12 ohm	1.00e+8 - 1.00e+12 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China