

## SABIC Innovative Plastics NORYL RN0401 PPE+PS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

**Material Notes:**

RN0401 is an unfilled Post Consumer Recycle (PCR) based injection moldable modified polyphenylene ether resin comprising at least 20% PCR styrenic series resin content. Available in black only.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-NORYL-RN0401-PPEPS-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-RN0401-PPEPS-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM D792
Density	1.11 g/cc	0.0401 lb/in <sup>3</sup>	ISO 1183
Melt Flow	30 g/10 min @Load 5.00 kg, Temperature 260 °C	30 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D1238
Melt Index of Compound	30 g/10 min @Load 5.00 kg, Temperature 260 °C	30 g/10 min @Load 11.0 lb, Temperature 500 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	35.0 MPa	5080 psi	50 mm/min; ISO 527
	40.0 MPa	5800 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	50.0 MPa	7250 psi	50 mm/min; ISO 527
	55.0 MPa	7980 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	15 %	15 %	Type I, 50 mm/min; ASTM D638
	15 %	15 %	50 mm/min; ISO 527
Elongation at Yield	3.0 %	3.0 %	Type I, 50 mm/min; ASTM D638
	3.0 %	3.0 %	50 mm/min; ISO 527
Tensile Modulus	2.10 GPa	305 ksi	5 mm/min; ASTM D638
	2.20 GPa	319 ksi	1 mm/min; ISO 527
Flexural Yield Strength	75.0 MPa	10900 psi	2 mm/min; ISO 178
	80.0 MPa	11600 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	1.00 J/cm	1.87 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	9.00 kJ/m <sup>2</sup>	4.28 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	70.0 Â°C	158 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	70.0 Â°C @Thickness 3.20 mm	158 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	94.0 Â°C	201 Â°F	Rate B/120; ISO 306
UL RTI, Electrical	65.0 Â°C	149 Â°F	UL 746B
UL RTI, Mechanical with Impact	65.0 Â°C	149 Â°F	UL 746B
UL RTI, Mechanical without Impact	65.0 Â°C	149 Â°F	UL 746B
Flammability, UL94	V-0 @Thickness 2.00 mm	V-0 @Thickness 0.0787 in	UL 94 by SABIC-IP

Electrical Properties	Metric	English	Comments
Dielectric Strength	25.0 kV/mm @Thickness 3.20 mm	635 kV/in @Thickness 0.126 in	in oil; ASTM D149
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	Tungsten; ASTM D495
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	UL 746A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China