

## SABIC Innovative Plastics NORYL WCV065 PPE+Polyolefin (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyolefin , Polyphenylene Ether/PPO

### Material Notes:

Flexible, non-halogenated FR, PPE+Polyolefin resin designed for evaluation in Automotive ISO6722 Class A-C applications.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-NORYL-WCV065-PPEPolyolefin-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-WCV065-PPEPolyolefin-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	20.2 g/10 min	20.2 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 280 Â°C	@Load 11.0 lb, Temperature 536 Â°F	
Melt Index of Compound	20 g/10 min	20 g/10 min	MVR [cm <sup>3</sup> /10 min]; ISO 1133
	@Load 5.00 kg, Temperature 280 Â°C	@Load 11.0 lb, Temperature 536 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	30S reading; ASTM D2240
Tensile Strength at Break	37.0 MPa	5370 psi	Type I, 50 mm/min; ASTM D638
	37.0 MPa	5370 psi	50 mm/min; ISO 527
Tensile Strength, Yield	37.0 MPa	5370 psi	Type I, 50 mm/min; ASTM D638
	39.0 MPa	5660 psi	50 mm/min; ISO 527
Elongation at Break	38 %	38 %	50 mm/min; ISO 527
	45 %	45 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	17 %	17 %	50 mm/min; ISO 527
	37 %	37 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	1.45 GPa	210 ksi	1 mm/min; ISO 527
Flexural Yield Strength	41.0 MPa	5950 psi	1.3 mm/min, 50 mm span; ASTM D790
	44.0 MPa	6380 psi	2 mm/min; ISO 178
Flexural Modulus	1.15 GPa	167 ksi	1.3 mm/min, 50 mm span; ASTM D790
	1.26 GPa	183 ksi	2 mm/min; ISO 178

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	9.50 J/cm	10.3 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	41.0 kJ/m <sup>2</sup>	19.5 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	9.00 kJ/m <sup>2</sup> @Temperature -30.0 °C	4.28 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	4.30 J/cm <sup>2</sup>	20.5 ft-lb/in <sup>2</sup>	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	33.0 J @Temperature 23.0 °C	24.3 ft-lb @Temperature 73.4 °F	ASTM D3763
	42.0 J @Temperature -30.0 °C	31.0 ft-lb @Temperature -22.0 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	82.0 Åµm/m-Å°C @Temperature -40.0 - 40.0 Å°C	45.6 Åµin/in-Å°F @Temperature -40.0 - 104 Å°F	ASTM E 831
CTE, linear, Transverse to Flow	131 Åµm/m-Å°C @Temperature -40.0 - 40.0 Å°C	72.8 Åµin/in-Å°F @Temperature -40.0 - 104 Å°F	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	115 Å°C @Thickness 3.20 mm	239 Å°F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	93.0 Å°C	199 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	84.0 Å°C @Thickness 3.20 mm	183 Å°F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	71.0 Å°C	160 Å°F	Rate B/50; ASTM D1525
	71.0 Å°C	160 Å°F	Rate B/50; ISO 306
	76.0 Å°C	169 Å°F	Rate B/120; ISO 306

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.5 @Frequency 1.00e+6 Hz	2.5 @Frequency 1.00e+6 Hz	IEC 60250

Electrical Properties	0.0020 Metric	0.0020 English	Comments
Dissipation Factor	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China