

SABIC Innovative Plastics Noryl NH3060 PPE+HIPS

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

NH3060 resin is a modified PPE + PS blend with an excellent balance of non-chlorinated non-brominated flame retardance, hydrolytic stability, impact and heat resistance, good flow, and low specific gravity for light-weight parts. This injection-molding resin is available in custom colors and meets UL 94 V-0 requirements at 1.5 mm. NH3060 may be an excellent candidate for industrial battery applications. This data was supplied by SABIC-IP for the Americas region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Noryl-NH3060-PPEHIPS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.11 g/cc	1.11 g/cc	ASTM D 792
Density	1.10 g/cc	0.0397 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.090 %	0.090 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	0.11 % @Temperature 23.0 ^o C	0.11 % @Temperature 73.4 ^o F	ISO 62
Linear Mold Shrinkage, Flow	0.0034 - 0.0052 cm/cm @Thickness 3.20 mm	0.0034 - 0.0052 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	32 g/10 min @Load 5.00 kg, Temperature 280 ^o C	32 g/10 min @Load 11.0 lb, Temperature 536 ^o F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	35.5 g/10 min @Load 5.00 kg, Temperature 280 ^o C	35.5 g/10 min @Load 11.0 lb, Temperature 536 ^o F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	53.0 MPa	7690 psi	Type I, 50 mm/min; ASTM D 638
	56.0 MPa	8120 psi	50 mm/min; ISO 527
Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527
	69.0 MPa	10000 psi	Type I, 50 mm/min; ASTM D 638
Elongation at Break	7.6 %	7.6 %	Type I, 50 mm/min; ASTM D 638
	9.5 %	9.5 %	50 mm/min; ISO 527
Elongation at Yield	4.0 %	4.0 %	Type I, 50 mm/min; ASTM D 638

Mechanical Properties	Metric	English	Comments
Tensile Modulus	2.72 GPa	395 ksi	5 mm/min; ASTM D 638
	2.97 GPa	431 ksi	1 mm/min; ISO 527
Flexural Yield Strength	105 MPa	15200 psi	1.3 mm/min, 50 mm span; ASTM D 790
	105 MPa	15200 psi	2 mm/min; ISO 178
Flexural Modulus	2.75 GPa	399 ksi	2 mm/min; ISO 178
	2.85 GPa	413 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	0.790 J/cm	1.48 ft-lb/in	ASTM D 256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.20 J/cm	2.25 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched (ISO)	7.00 kJ/m ²	3.33 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	10.0 kJ/m ²	4.76 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.10 J/cm ²	5.23 ft-lb/in ²	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	36.0 J	26.6 ft-lb	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	69.0 µm/m-°C	38.3 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	69.0 µm/m-°C	38.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	73.0 µm/m-°C	40.6 µin/in-°F	ASTM E 831

Thermal Properties	Metric @Temperature -40.0 - 40.0 Â°C	English @Temperature -40.0 - 104 Â°F	Comments
	73.0 Âµm/m-Â°C	40.6 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	93.0 Â°C	199 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	92.0 Â°C	198 Â°F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	114 Â°C	237 Â°F	Rate B/50; ASTM D 1525
	114 Â°C	237 Â°F	Rate B/50; ISO 306
	116 Â°C	241 Â°F	Rate B/120; ISO 306
Flammability, UL94	V-0	V-0	UL 94 by SABIC-IP
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.60e+16 - 4.30e+16 ohm-cm	2.60e+16 - 4.30e+16 ohm-cm	ASTM D 257
Dielectric Constant	2.3	2.3	ASTM D 150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	27.7 kV/mm	704 kV/in	in air; ASTM D 149
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Dissipation Factor	0.0030	0.0030	ASTM D 150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	225 V	225 V	IEC 60112
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	PLC code 2; UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	surface, PLC code 1; UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China