

## **SABIC Innovative Plastics PPO 630 PPO (Europe-Africa-Middle East)**

Category: Polymer, Thermoplastic, Polyphenylene Ether/PPO

## **Material Notes:**

PPO\* 630 resin is a medium molecular weight polymer based on Polyphenylene Ether (PPE). PPO\* is intended for use as an additive or a building block in a variety of thermoplastics and thermoplastic elastomers like Styrenic Block Copolymers. PPO\* resin can be used to improve properties like Heat Distortion and Creep Resistance. It is hydrolytically stable and non-hydroscopic (typically less than 0.2% water uptake). The polymer is soluble in common organic solvents like toluene, chloroform, and THF. Chemical name: Poly (2,6-dimethyl-, 1,4-phenylene ether) (PPE) Formula: (C8H8O)n Regulatory Status: Complies with the FDA regulation 21CFR 177..2460. Also complies with EU Directive 2002/72/EC.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_SABIC-Innovative-Plastics-PPO-630-PPO-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Bulk Density	0.462 g/cc	0.0167 lb/in³	ISO 1183
Particle Size	190 μm	190 μm	SABIC Method
Viscosity Measurement	0.33	0.33	Intrinsic Viscosity [dl/g]; SABIC Method
Molecular Weight	47600 g/mol	47600 g/mol	Mw; SABIC Method

Thermal Properties	Metric	English	Comments
Transformation Temperature, Tg	214 °C	417 °F	half width; SABIC Method

Descriptive Properties	Value	Comments
Mn	17300	SABIC Method
Phenolic End-group Content	1180ppm	SABIC Method
Physical Form	POWDER	SABIC Method
Toluene Content	<1500ppm	SABIC Method

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China