

SABIC Innovative Plastics PPO 646 PPO (Asia Pacific)

Category: Polymer, Thermoplastic, Polyphenylene Ether/PPO

Material Notes:

PPO* 646 resin is a high molecular weight polymer based on Polyphenylene Ether (PPE). PPO* is intended for use as an additive or a building block in a variety of thermoplastics and thermoplastic elastomers like Styrenic Block Copolymers. PPO* resin can be used to improve properties like Heat Distortion and Creep Resistance. It is hydrolytically stable and non-hydroscopic (typically less than 0.2% water uptake). The polymer is soluble in common organic solvents like toluene, chloroform, and THF. Chemical name: Poly (2,6-dimethyl-, 1,4-phenylene ether) (PPE) Formula: (C8H8O)n Regulatory Status: Complies with the FDA regulation 21CFR 177..2460. Also complies with EU Directive 2002/72/EC.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-PPO-646-PPO-Asia-Pacific.php

| Physical Properties | Metric | English | Comments |
|-----------------------|-------------|---------------------------|---|
| Bulk Density | 0.465 g/cc | 0.0168 lb/in ³ | ISO 1183 |
| Particle Size | 200 μm | 200 μm | SABIC Method |
| Viscosity Measurement | 0.46 | 0.46 | Intrinsic Viscosity [dl/g]; SABIC Method |
| Molecular Weight | 68600 g/mol | 68600 g/mol | Mw; SABIC Method |

| Thermal Properties | Metric | English | Comments |
|--------------------------------|--------|---------|--------------------------|
| Transformation Temperature, Tg | 217 °C | 423 °F | half width; SABIC Method |

| Descriptive Properties | Value | Comments |
|----------------------------|----------|--------------|
| Mn | 21700 | SABIC Method |
| Phenolic End-group Content | 820ppm | SABIC Method |
| Physical Form | POWDER | SABIC Method |
| Toluene Content | <1500ppm | SABIC Method |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China