

SABIC Innovative Plastics ULTEM 2210 PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

20% Glass fiber filled, enhanced flow Polyetherimide (Tg 217C). ECO Conforming, UL94 V0 and 5VA listing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-2210-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.42 g/cc	1.42 g/cc	ASTM D792
Melt Flow	8.4 g/10 min	8.4 g/10 min	ASTM D1238
	@Load 6.60 kg, Temperature 337 Â°C	@Load 14.6 lb, Temperature 639 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	114	114	ASTM D785
Tensile Strength at Break	139 MPa	20200 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	6.89 GPa	999 ksi	5 mm/min; ASTM D638
Flexural Strength	227 MPa	32900 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	6.89 GPa	999 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	0.640 J/cm	1.20 ft-lb/in	ASTM D256
	4.53 J/cm @Thickness 3.20 mm	8.49 ft-lb/in @Thickness 0.126 in	ASTM D256
Izod Impact, Unnotched	4.75 J/cm	8.90 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	210 Â°C	410 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	211 Â°C	412 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	225 Â°C	437 Â°F	Rate B/50; ASTM D1525
Glass Transition Temp, Tg	217 Â°C	423 Â°F	

Thermal Properties	Metric	English	Comments
UL RTI, Mechanical with Impact	170 Â°C	338 Â°F	UL 746B
UL RTI, Mechanical without Impact	170 Â°C	338 Â°F	UL 746B
Flammability, UL94	V-0	V-0	UL 94
	@Thickness 0.400 mm	@Thickness 0.0157 in	
	5VA	5VA	UL 94
	@Thickness 1.90 mm	@Thickness 0.0748 in	
Oxygen Index	50 %	50 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Arc Resistance	60 - 120 sec	60 - 120 sec	Tungsten; ASTM D495
Comparative Tracking Index	100 - 175 V	100 - 175 V	UL 746A
Hot Wire Ignition, HWI	60 - 120 sec	60 - 120 sec	UL 746A
High Amp Arc Ignition, HAI	0.00 - 15 arcs	0.00 - 15 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

Descriptive Properties	Value	Comments
NBS Smoke Density, Flaming, Ds 4 min	1.3	ASTM E 662

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China