

SABIC Innovative Plastics ULTEM HU2310 PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

30% Glass fiber filled, enhanced flow Polyetherimide (Tg 217C). ECO Conforming. For medical devices and pharmaceutical applications.

Healthcare management of change, biocompatible (ISO 10993 or USP Class VI), food contact compliant.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-HU2310-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.51 g/cc	1.51 g/cc	ASTM D792
Density	1.51 g/cc	0.0546 lb/in ³	ISO 1183
Moisture Absorption	0.500 %	0.500 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	0.90 %	0.90 %	ISO 62
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm @Thickness 3.20 mm	0.0020 - 0.0040 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	7.6 g/10 min @Load 6.60 kg, Temperature 337 ^o C	7.6 g/10 min @Load 14.6 lb, Temperature 639 ^o F	ASTM D1238
Melt Index of Compound	8.0 g/10 min @Load 5.00 kg, Temperature 360 ^o C	8.0 g/10 min @Load 11.0 lb, Temperature 680 ^o F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	158 MPa	22900 psi	Type I, 5 mm/min; ASTM D638
	165 MPa	23900 psi	5 mm/min; ISO 527
Tensile Strength, Yield	165 MPa	23900 psi	5 mm/min; ISO 527
	168 MPa	24400 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	2.0 %	2.0 %	5 mm/min; ISO 527
	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	9.23 GPa	1340 ksi	5 mm/min; ASTM D638

Mechanical Properties	9.50 GPa Metric	1380 ksi English	1 mm/min; ISO 527 Comments
Flexural Yield Strength	220 MPa	31900 psi	1.3 mm/min, 50 mm span; ASTM D790
	225 MPa	32600 psi	2 mm/min; ISO 178
Flexural Modulus	8.50 GPa	1230 ksi	2 mm/min; ISO 178
	9.25 GPa	1340 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.850 J/cm	1.59 ft-lb/in	ASTM D256
	0.900 J/cm @Temperature -30.0 Â°C	1.69 ft-lb/in @Temperature -22.0 Â°F	ASTM D256
Izod Impact, Notched (ISO)	10.0 kJ/mÂ²	4.76 ft-lb/inÂ²	80*10*4; ISO 180/1A
	10.0 kJ/mÂ² @Temperature -30.0 Â°C	4.76 ft-lb/inÂ² @Temperature -22.0 Â°F	80*10*4; ISO 180/1A
Charpy Impact, Notched	1.00 J/cmÂ²	4.76 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	10.0 J	7.38 ft-lb	ASTM D3763
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	16.0 Âµm/m-Â°C	8.89 Âµin/in-Â°F	ASTM E 831
	@Temperature -20.0 - 150 Â°C	@Temperature -4.00 - 302 Â°F	
	16.0 Âµm/m-Â°C	8.89 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	
CTE, linear, Transverse to Flow	41.0 Âµm/m-Â°C	22.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -20.0 - 150 Â°C	@Temperature -4.00 - 302 Â°F	
	41.0 Âµm/m-Â°C	22.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	210 Â°C	410 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	208 Â°C	406 Â°F	unannealed; ASTM D648

Thermal Properties	@Thickness 3.20 mm Metric	@Thickness 0.126 in English	Comments
	210 Å°C	410 Å°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	213 Å°C	415 Å°F	Rate B/50; ISO 306
	220 Å°C	428 Å°F	Rate B/120; ISO 306
	228 Å°C	442 Å°F	Rate B/50; ASTM D1525
Glass Transition Temp, Tg	217 Å°C	423 Å°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China