

## SABIC Innovative Plastics ULTEM XH6050 PEI Copolymer

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

### Material Notes:

Transparent, enhanced flow Polyetherimidesulfone copolymer (Tg 247C). ECO Conforming, UL94 V0 listing. Resin is subject to U.S. Commerce Control Laws (15CFR Chapter VII, Part 774).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-ULTEM-XH6050-PEI-Copolymer.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-XH6050-PEI-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792
Density	1.30 g/cc	0.0470 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.600 %	0.600 %	23 <sup>o</sup> C / 50% RH; ISO 62
Water Absorption at Saturation	1.75 %	1.75 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	12.5 g/10 min @Load 6.60 kg, Temperature 367 <sup>o</sup> C	12.5 g/10 min @Load 14.6 lb, Temperature 693 <sup>o</sup> F	ASTM D1238
Melt Index of Compound	8.0 g/10 min @Load 5.00 kg, Temperature 360 <sup>o</sup> C	8.0 g/10 min @Load 11.0 lb, Temperature 680 <sup>o</sup> F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	140 MPa	20300 psi	ISO 2039-1
Tensile Strength at Break	78.0 MPa	11300 psi	5 mm/min; ISO 527
	96.0 MPa	13900 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	95.0 MPa	13800 psi	5 mm/min; ISO 527
	96.0 MPa	13900 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	16.8 %	16.8 %	5 mm/min; ISO 527
	25 %	25 %	Type I, 5 mm/min; ASTM D638

Mechanical Properties	Metric	English	Comments
Elongation at Yield	8.5 %	8.5 %	Type I, 5 mm/min; ASTM D638
			5 mm/min; ISO 527
Tensile Modulus	3.11 GPa	451 ksi	1 mm/min; ISO 527
	3.51 GPa	509 ksi	5 mm/min; ASTM D638
Flexural Strength	159 MPa	23100 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Yield Strength	123 MPa	17800 psi	2 mm/min; ISO 178
	155 MPa	22500 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	3.08 GPa	447 ksi	2 mm/min; ISO 178
	3.17 GPa	460 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.690 J/cm	1.29 ft-lb/in	ASTM D256
	0.740 J/cm	1.39 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched	NB	NB	ASTM D4812
Izod Impact, Notched (ISO)	4.00 kJ/m <sup>2</sup>	1.90 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	5.00 kJ/m <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*4; ISO 180/1U
	NB	NB	80*10*4; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	33.0 J	24.3 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	English $\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	Comments
CTE, linear, Parallel to Flow	@Temperature -40.0 - 150 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 302 $\text{Å}^\circ\text{F}$	ASTM E 831
	50.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	27.8 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
CTE, linear, Transverse to Flow	@Temperature -40.0 - 150 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 302 $\text{Å}^\circ\text{F}$	ASTM E 831
	50.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	27.8 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ISO 11359-2
Thermal Conductivity	0.220 W/m-K	1.53 BTU-in/hr-ft $\text{Å}^2\cdot\text{Å}^\circ\text{F}$	ASTM E 1530
Deflection Temperature at 0.46 MPa (66 psi)	237 $\text{Å}^\circ\text{C}$	459 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	228 $\text{Å}^\circ\text{C}$	442 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af
	217 $\text{Å}^\circ\text{C}$	423 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
	230 $\text{Å}^\circ\text{C}$	446 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	238 $\text{Å}^\circ\text{C}$	460 $\text{Å}^\circ\text{F}$	Rate B/120; ISO 306
	242 $\text{Å}^\circ\text{C}$	468 $\text{Å}^\circ\text{F}$	Rate B/50; ASTM D1525
	242 $\text{Å}^\circ\text{C}$	468 $\text{Å}^\circ\text{F}$	Rate B/50; ISO 306
Glass Transition Temp, Tg	247 $\text{Å}^\circ\text{C}$	477 $\text{Å}^\circ\text{F}$	
Oxygen Index	45 %	45 %	ISO 4589
Glow Wire Test	850 $\text{Å}^\circ\text{C}$	1560 $\text{Å}^\circ\text{F}$	IEC 60695-2-13
	960 $\text{Å}^\circ\text{C}$	1760 $\text{Å}^\circ\text{F}$	IEC 60695-2-12
	@Thickness 3.20 mm	@Thickness 0.126 in	
Optical Properties	Metric	English	Comments
Haze	2.0 %	2.0 %	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Dielectric Strength	17.0 kV/mm	432 kV/in	in oil; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0010	0.0010	IEC 60250
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.0070	0.0070	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.0080	0.0080	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.025	0.025	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Comparative Tracking Index	175 V	175 V	IEC 60112

Descriptive Properties	Value	Comments
Ball Pressure Test, 125Â°C +/- 2Â°C	Passes	IEC 60695-10-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China