

SABIC Innovative Plastics Valox[®] EH7020 PBT (Asia Pacific)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Valox-EH7020-PBT-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.49 g/cc	1.49 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.014 - 0.016 cm/cm	0.014 - 0.016 in/in	SABIC Method
	@Thickness 1.50 - 3.20 mm	@Thickness 0.0591 - 0.126 in	
	0.015 - 0.016 cm/cm	0.015 - 0.016 in/in	SABIC Method
	@Thickness 3.20 - 4.60 mm	@Thickness 0.126 - 0.181 in	
Linear Mold Shrinkage, Transverse	0.013 - 0.014 cm/cm	0.013 - 0.014 in/in	SABIC Method
	@Thickness 1.50 - 3.20 mm	@Thickness 0.0591 - 0.126 in	
	0.014 - 0.015 cm/cm	0.014 - 0.015 in/in	SABIC Method
	@Thickness 3.20 - 4.60 mm	@Thickness 0.126 - 0.181 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	57.0 MPa	8270 psi	Type I, 5 mm/min; ASTM D638
Flexural Strength	103 MPa	14900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	4.13 GPa	599 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.320 J/cm	0.599 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.89 J/cm	7.29 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	55.8 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	31.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	187 $\text{Å}^\circ\text{C}$	369 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Thermal Properties (264 psi)	Metric	English	Comments
Temperature at 1.8 MPa	105 A°C	221 A°F	ASTM D638, ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.9	2.9	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.1	3.1	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	16.9 kV/mm	429 kV/in	in oil; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0039	0.0039	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.014	0.014	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China