

SABIC Innovative Plastics Valox[®] V8280 PBT+PET (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , PBT + PET Blend, Glass Filled , Polyethylene Terephthalate (PET)

Material Notes:

40% GR PBT+PET. High stiffness. Excellent surface aesthetics. Applications include office furniture.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Valox-V8280-PBTPET-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.64 g/cc	1.64 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	33 g/10 min	33 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 266 Â°C	@Load 11.0 lb, Temperature 511 Â°F	
Melt Index of Compound	22 g/10 min	22 g/10 min	MVR [cm ³ /10 min]; ISO 1133
	@Load 5.00 kg, Temperature 265 Â°C	@Load 11.0 lb, Temperature 509 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	145 MPa	21000 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	2.2 %	2.2 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	2.2 %	2.2 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	12.75 GPa	1849 ksi	5 mm/min; ASTM D638
Flexural Strength	220 MPa	31900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	10.68 GPa	1549 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.06 J/cm	1.99 ft-lb/in	ASTM D256
Izod Impact, Unnotched	8.27 J/cm	15.5 ft-lb/in	ASTM D4812
	7.00 J	5.16 ft-lb	

Mechanical Properties	Metric	English	Comments
	@ Temperature 23.0 Â°C	@ Temperature 73.4 Â°F	ASTM D2753

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	14.4 Âµm/m-Â°C @Temperature -40.0 - 40.0 Â°C	8.00 Âµin/in-Â°F @Temperature -40.0 - 104 Â°F	ASTM E 831
CTE, linear, Transverse to Flow	73.8 Âµm/m-Â°C @Temperature -40.0 - 40.0 Â°C	41.0 Âµin/in-Â°F @Temperature -40.0 - 104 Â°F	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	215 Â°C @Thickness 3.20 mm	419 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	193 Â°C @Thickness 3.20 mm	379 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	221 Â°C	430 Â°F	Rate B/50; ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China